



## TECHNICAL DATA SHEET

**Actymer G GA-1070A-US BLK**

(Thermo Plastic Vulcanizate)

## General Characteristics

**Description :** GA-1070A-US BLK is a Thermoplastic Vulcanized compound.**Feature :** Low compression set and ease of processing.**Process :** Injection Molding, Coextrusion, Multi Injection Molding**Applications :** Automotive, Industrial, Seals and Gaskets, General purpose**Available Color(s) :** BLACK

## Technical Information

PHYSICAL	Typical Value <sup>1</sup>	Unit	
Form		Pellet	
Specific Gravity ( $\pm 0.03$ )	0.94		ISO 1183
Hardness (Shore 'A', $\pm 5$ , 15 sec)	67		ISO 868
<b>MECHANICAL</b>			
Tensile Strength	6.0 MPa		ISO 37
100% Modulus	3.2 MPa		
Ultimate Elongation	380 %		
<b>Compression set</b>			
after 22 hours at 70 °C (158°F)	35 %		ISO 815
<b>MELT FLOW</b>			
MFR 230°C (446°F) 5 kg	5.0 g/10 min		ISO 1133
<b>Thermal</b>			
Brittleness	Less than -60 °C (-76°F)		ISO 974

**PROCESSING**

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	180 ° F	80 °C
Drying Time	3.0 hr	3.0 hr
Suggested Max Moisture	0.05 %	0.05 %
Suggested Max Re grind	20 %	20 %
Rear Temperature	320 to 392 ° F	160 to 200 °C
Middle Temperature	374 to 446 ° F	190 to 230 °C
Front Temperature	374 to 446 ° F	190 to 230 °C
Nozzle Temperature	392 to 446 ° F	200 to 230 °C
Processing(Melt) Temp	374 to 446 ° F	190 to 230 °C
Mold Temperature	86 to 122 ° F	30 to 50 °C
Injection Rate	Fast	Fast
Back Pressure	50 to 100 psi	0.3 to 0.7 MPa
Screw Speed	100 to 200 rpm	100 to 200 rpm
<b>Extrusion</b>		
Drying Temperature	180 ° F	80 °C
Drying Time	3.0 hr	3.0 hr
Melt Temperature	374 to 446 ° F	190 to 230 °C
Die Temperature	374 to 446 ° F	190 to 230 °C

**REGULATORY**

N/A

---

**Additional Information**

Where applicable, test results based on film gated, 2.0mm injection molded plaques. Tensile strength, elongation and tensile stress are measured across the flow direction. Compression set at 25% deflection.

---

**Notes**

<sup>1</sup> Typical Values: These are not construed as specifications; values may vary depending on colors.



*IMPORTANT: These suggestions and data are based on information we believe to be reliable. They are offered in good faith without guarantee or warranty, as conditions and methods of use of our products are beyond our control. We strongly urge that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale. User assumes all risks and liabilities in connection with use*