Revision Date: 11-6-2019 Page 1 of 1



TECHNICAL DATA SHEET

Multiuse Leostomer LJ-3140N-US

(Olefin-based Thermoplastic Elastomer)

General Characteristics

Description: LJ-3140N-US is a Thermoplastic Elastomer compound.

Feature: Ease of Injection processing. **Application:** General purpose Injection.

Available Color(s): Black and Natural

Technical Information		
PHYSICAL	Typical Value ¹ Unit	
Form	Pellet	
Specific Gravity (± 0.03)	0.94	ISO 1183
Hardness (Shore 'A', ± 5, 15 sec)	40	ISO 868
MECHANICAL		
Tensile Strength	8.5 MPa	ISO 37
100% Modulus	1.0 MPa	ISO 37
Ultimate Elongation	980 %	ISO 37
Tear Strength	26 N/mm	ISO 34-1
Elasticity		
Compression set		
after 22 hours at 70 °C (158°F)	32 %	ISO 815
Thermal		
Brittleness	Less than -60 °C (-76°F)	ISO 974
Aging		
Retention in Tensile Stress (50°C (122°F), 24 hr, in IRM 902 Oil)	89 %	ISO 1817
Volume Swell(50°C, (122°F) 24 hr, in IRM 902 Oil)	13 %	ISO 1817
MELT FLOW		_
MFR 230°C (446°F) 2,160g	3.4 g/10 min	ISO 1133
PROCESSING		
Method	Extrusion	
Recommended Melt Temperature	200 °C (392 °F)	

REGULATORY

N/A



¹ Typical Values: These are not construed as specifications.

IMPORTANT: These suggestions and data are based on information we believe to be reliable. They are offered in good faith without guarantee or warranty, as conditions and methods of use of our products are beyond our control. We strongly urge that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale. User assumes all risks and liabilities in connection with use of this product.

² Type 1A tensile bars. Speed of testing: 500mm/min